



常州隽隆复合材料有限公司

CHANGZHOU JLON COMPOSITE CO.,LTD

FuHan Yuan 1-820,New North District,Changzhou 213022,Jiangsu,China

Tel:86-519-89810829

Email:info@jloncomposite.com



### Technical Data Sheet

Product name	Nylon Bagging Film	
Type	BF150(75um)	
Item	Unit	Standard
Width	m m	±5
Thickness	m m	±5%
Longitudinal tensile strength	MPA	≥40
Transverse tensile strength	MPA	≥40
Tear strength at right angle	N/cm	> 100
Heat Seal Strength	N/15mm	≥25
Temperature resistance	°C	140°C
Color	Yellow	
Remark	Oven 140 °C constant temperature for 3 hours without deformation, good barrier properties, vacuum holding pressure 10 minutes to reduce 1000 Pa.	

Disclaimer: All of the above data is our company in specific conditions of the test obtained, in view of the actual operation of the process and other factors affecting the data does not replace the user's own investigation and testing, we can not make a guarantee for a variety of individual special circumstances, in the use of the company's products before the use of the target to carry out the performance of the test due to ensure that the use of the company's products.