



常州隼隆复合材料有限公司

CHANGZHOU JLON COMPOSITE CO.,LTD

FuHan Yuan 1-820,New North District,Changzhou 213022,Jiangsu,China

Tel:86-519-89810829

Email:info@jloncomposite.com



Technical Data Sheet

Sealant Tape

Physical Property	Units	Specification	Test Method
Thickness	mm	3	
Width	mm	12	
Length	m	15	
Color	-	Yellow	
Material	-	Sythetic Butyl Rubber	
Working Temperature	C	Max 200	
Elongation	%	680	ASTM C736
Peel strength	300mm/Min @23C	Glass \geq 16.3	ASTM D3330
	300mm/Min @23C	Stainless Steel \geq 12.5	ASTM D3330
Shear strength	250mm/Min @23C	Glass \geq 35	GB/T12952
		Stainless Steel \geq 37	